

PHYSICAL PROPERTIES OF ISO-C1/2.5 POLYISOCYANURATE RIGID FOAM INSULATION

PHYSICAL PROPERTY MEASURED ⁽¹⁾	ASTM METHOD ⁽²⁾	VALUE	PHYSICAL PROPERTY MEASURED	ASTM METHOD ⁽²⁾	VALUE
Density ⁽³⁾	D-1622	2.5 lb/cu ft	Dimensional Stability ^{(3) (5)}	D-2126	
Compressive Strength ⁽³⁾	D-1621		@ 158°F/97%RH, 7 Days	Length	Less Than +1.0%
Parallel to rise		37 lbs/sq in			
Perpendicular to rise	T	31 lbs/sq in	@ 212°F, 7 Days	Volume	Less Than +1.2%
Tensile Strength	D-1623	43 lbs/sq in		Length	Less Than +0.2%
Flexural Strength	C-203	56 lbs/sq in	@ -40°F, 7 Days	Volume	Less Than +0.1%
Flexural Modulus	C-203	961 lbs/sq in		Length	Less Than +0.1%
Shear Strength	C-273	26 lbs/sq in	Water Absorption	C-272	Less Than +0.1%
Shear Modulus	C-273	253 lbs/sq in	Water Vapor Permeability	E-96	2.23 perm-in
			Service Temperature ⁽⁴⁾ °F(°C)		-297 to +300 (-183 to +149)
Thermal Conductivity/Resistance	C-518		Surface Burning Characteristics ⁽⁶⁾		
10 days K-Factor	@ 1"	0.15			
Aged K-Factor	@ 1"	0.18	Flame spread @ 4"	E-84	25
Aged R-Factor	@ 1"	5.6	Smoke density @ 4"	E-84	160
Closed Cell Content	D-2856	> 98%	Hot Surface	C-411	TBD

⁽¹⁾ All properties are measured at 70°F – 75°+ unless otherwise indicated and all test values from independent certified testing laboratories.

⁽²⁾ These are nominal values obtained from representative product samples, and are subject to normal manufacturing variances.

⁽³⁾ Average value through the foam cross section.

⁽⁴⁾ Above 300°F, discoloration and charring will occur, resulting in an increased K-Factor in the discolored area.

⁽⁵⁾ Frequent and severe thermal cycling can produce dimensional changes significantly greater than those listed here. Special design considerations must be made in systems subject to severe cycling.

⁽⁶⁾ This numerical flame spread data is not intended to reflect hazards presented by this or any other material under actual fire conditions.

FOR TECHNICAL INFORMATION:



(800) 433-5551
info@dyplastproducts.com
www.dyplastproducts.com
 12501 N.W. 38th Ave.
 Miami, FL 33054

- **Contact: Michael Cartmell**
Vice President, Technology
- **Phone: (305) 921-0123 Fax: (305) 687-6353**
- **Email: mcartmell@dyplastproducts.com**
- **MSDS sheets available upon request**

NOTICE: No freedom from any patent owned by Dyplast Products or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. Dyplast Products assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

LIMITATIONS AND DISCLAIMER OF WARRANTIES AND LIABILITIES

Characteristics, properties, performance of materials, and application specifications herein described are based on data obtained under controlled conditions. Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. Dyplast Products makes no implied warranties of any type, including without limitation, any warrant of merchantability or fitness of purpose. In no event will Dyplast Products be responsible for damages of any nature whatsoever resulting from the use of or reliance upon this information or the product to which information refers. No agent, sales representative, or employee is empowered to change, alter, or amend this provision, unless approved in writing by a duly authorized officer of Dyplast Products.